

RUBBERBOND

ADHESIVES & SEALANTS

RubberBond Bonding Adhesive

is a high-strength, solvent-based contact adhesive that allows quick bonding of cured flashings and membranes to various substrates. This adhesive is specially formulated for application with a spreader brush or medium nap roller. This Bonding Adhesive is designed for bonding RubberBond EPDM to various substrates.



Typical Properties and Characteristics

Base	Synthetic Rubber
Color	Beige
Solids	21%
Flash Point	-22° C Closed Cup
Average Brookfield Viscosity	3750 Centipoise
Packaging	5 litre pail
Shelf Life	1 year

WBA Deck Adhesive

is a high-strength, water-based adhesive that allows quick bonding of RubberBond membranes to various substrates.



Typical Properties and Characteristics

Base	Acrylic
Color	Liquid - White Dried Film - Brown
Average Solids	50%
Flash Point	None
Average Viscosity	16,000 Centipoise
Packaging	16 litre Pail
Shelf Life	1 Year

Weathered Membrane Cleaner

is used to clean in-service EPDM membrane that has been exposed to the weather. It helps to loosen and remove dirt and other contaminants from the surface of the EPDM membrane and leaves a suitable surface for seaming and the subsequent application of HP-250 Primer.



Typical Properties and Characteristics

Color	Clear
Solids	0%
Flash Point	55° F (13° C)
Boiling Point	246° F (119° C)
Packaging	5 (18.9 liters) gallon closed top pail
VOC	755 grams/liter

RubberBond PU Deck Adhesive

is a component moisture curing polyurethane adhesive used for bonding RubberBond membranes to various surfaces. This adhesive is resistant to high and low temperatures with a fast curing time.



Typical Properties and Characteristics

Base	Polyurethane
Color	Blue liquid
Average Solids	85%
Flash Point	-1° C
Average Viscosity	8000 Centipoise
Packaging	10 litre poly bottles
Shelf Life	6 Months

Roofing the World for Over 50 Years

Exclusive UK & Ireland distributors for Carlisle-Syntec and RubberBond EPDM

- Email: enq@rubberbond.co.uk • www.rubberbond.co.uk
- Tel: +44 (0) 1494 448792 • +44 (0) 1494 465393
- Flex-R Ltd., Unit 5 Central Park, Bellfield Road, High Wycombe, Bucks. HP13 5HG



Roofing the world for over 50 years

RUBBERBOND

ADHESIVES & SEALANTS



HP-250 Primer

is a solvent-based product designed for one-step cleaning and priming of EPDM surfaces prior to the application of SecurTAPE™ and all other pressure-sensitive products. HP-250 can also be used with EP-95 Splicing Cement.

Typical Properties and Characteristics

Base	Synthetic Rubber
Color	Bronze to Olive drab
Solids	18%
Flash Point	40° F (4.4° C)
VOC	727 grams/liter
Packaging	1 gallon (3.8 liters) cans or 2½ gallon (9.5 liter) pails
Shelf Life	6 months
Average Weight	7.4 lbs./gallon (3.4 kg/gallon)



RubberBond Lap Sealants

are heavy-bodied trowel or gun consistency materials used in conjunction with roofing system materials. Its primary use is to seal the exposed edges of EPDM membrane splices. Lap Sealants are extremely durable. The cured rubber consistency enables it to expand and contract with the membrane.

Sure-Seal Lap Sealant is to be used to seal splice edges of cured Sure-Seal EPDM and uncured EPDM Elastoform Flashing.

Water Cut-Off Mastic

is a one-component, low viscosity, self-wetting butyl blend mastic used with roofing and waterproofing systems and also when the membrane is being terminated using a compression-type seal.



Typical Properties and Characteristics

Color	Gray
Solids	80%
Flash Point	40° F (4° C) Closed Cup
Service Temp.	-40° F to 200° F (-40° C to 93° C)
Specific Gravity	1.29
Cold Weather Flex	Excellent
Average Brookfield Viscosity	1,320,000 cps
Packaging	10 tubes/Carton, 5 gallon pails
VOC	250 grams/liter
Clean up	Weathered Membrane Cleaner
Average Net Weight/gallon	10.7 lbs. (4.9 Kg/gallon)
Shelf Life	1 year, unopened container

Typical Properties and Characteristics

Color	Black
Flash Point	- 40° F (4° C) Tag Open Cup
Service Temp.	-60° F to 180° F (-51° C to 82° C)
Specific Gravity	1.03
Cold Weather Flex.	Excellent
Resistance to Staining General	Excellent
Weathering Ozone Ultraviolet	Excellent
Radiation Slump Water Acid Alkali	Very Good Excellent Good Good
VOC	395 grams/liter
Average Net Weight/gallon	8.58 lbs. (3.9 Kg)
Packaging	25 Tubes/Carton, 5 gallon pails
Shelf Life	1 year

Roofing the World for Over 45 Years

Exclusive UK & Ireland distributors for Carlisle-Syntec and RubberBond EPDM

- Email: enq@rubberbond.co.uk • www.rubberbond.co.uk
- Tel: +44 (0) 1494 448792 • +44 (0) 1494 465393
- Flex-R Ltd., Unit 5 Central Park, Bellfield Road, High Wycombe, Bucks. HP13 5HG



Roofing the world for over 45 years

